



LINEA	Resellers
Scheda n°	45.207
Rev.	1
Anno	August 2013
PRODOTTO	<b>ATRIAFLOOR IN   OUT RESINA COLORATA</b>

#### Tipo di Prodotto

**Equalizing coloured resin in paste for IN | OUT cycle, walls and floors.**

**Atriafloor IN | OUT RESINA COLORATA** is a modified acrylic-polyurethane resin in aqueous emulsion and with controlled particle size aggregates, free from salts and impurities. Due to its high filling power and ease of application and levelling, it is also suitable as a coloured filler resin to be applied over Atriafloor Rasante One, for low-shrinkage no cracking interiors and exteriors.

#### Campi di Impiego

Specific for the finishing of interior and exterior floors and walls - IN | OUT cycle

Caratteristiche tecniche	Appearance	Pasty
	Pot colour	Secondo cartella colori
	Density Kg/Lt	1,45 ± 0,05
	Viscosity as supplied 25°C	25000 + / -4000 m Pa s.
	Volumetric dry residue %	70 ± 2%
	Theoretical spreading rate	300 - 350 gr./m² for coat
	Recommended minimum thickness	Minimum 0,35 mm
	Dilution	Water if necessary max 1 - 2% during cold periods
	<b>APPLICATION METHOD</b>	Spatula or trowel
	<b>DRYING 25°C</b>	
	Dry to touch	2 hours
	Dry in Depth	4 hours
	Dry sanding	12 hours
	Recoating Minimum / Maximum	After 12 hours
	Flash point	Not fuammable
	Cold resistance	Until -30°C tested
	Storage stability	24 months
	Standard packages	15 Kg - 5 Kg - 1 Kg

LINEA	Resellers
Scheda n°	45.207
Rev.	1
Anno	August 2013
PRODOTTO	<b>ATRIAFLOOR IN   OUT RESINA COLORATA</b>

**AtriaFloor®**  
resin decorations

#### Application method

#### Surface Preparation

*On absorbent surfaces such as:* Concrete, uneven cement mortar or rough plaster, apply a first coat of Atriafloor Consolidante, Atriafloor Rasante One and then **Atriafloor IN | OUT Resina colorata**.

*On non-absorbent surfaces:* Floors made of ceramic, terracotta (dewaxed), cement slabs, apply a first coat of Atriafloor Primer, Atriafloor Rasante One and then **Atriafloor IN | OUT Resina colorata**.

Apply **Atriafloor IN | OUT Resina colorata** with a steel spatula and distribute the product evenly over the entire surface, apply a second coat of finish after 4 hours if necessary.

**Caution:** on floors with joints it is important to close, fill and level the surface with the products listed above, in the case of wide and deep joints it is necessary to apply multiple coats to achieve an even surface.

#### Recommended for

Interior and exterior surfaces

#### Not recommended for

How to finish as it is, walkable

#### Recommended Undercoats and finishes

**IN | OUT Cycle Atriafloor**

#### Safety information

It is not a dangerous product and it is free from safety labelling according to EEC Directive 88/379.

For more information, refer to the corresponding safety data sheet.

(\*) This information, despite being deemed reliable, must be regarded as indicative, the company reserves the right to change it without notice. The use of this information does not imply any responsibility on our part, including the violation of any license. It is the users' responsibility to check the suitability of the product for the specific use in advance. For further clarification or specific questions regarding products please contact the technical laboratory manager.