



Atriapol

Atriafloor Protettivo

Linea: Rivenditori Numero : 13 Revisione: 1 Anno : Aprile 2013

Product Type **Two-component protective coating**
Atriafloor Protettivo, matt, shine is a protective water-based coating with excellent physical-mechanical features, chemical resistance to solvents and cleaning solutions for domestic and industrial use, mineral and vegetable oils, fuels.

Area to be used For surfaces with Atriafloor resin

Technical Specifications	Look	Matt - Shine
	Color inside the tin can	Milk
	Density kg./l.	1,15 ± 0,05
	Viscosity of supply 25°c	120 seconds – DIN 4
	Volume dry residue %	37 – 38 %
	Theoretical yield	180 gr /m2 in two coats
	Micron regular thickness Wet / Dry	100 / 38
	Mixing ratio Base / Hardener	90 : 10
	Pot Life	8 hours at 25° C
	Dilution	Water 20%
	Tool cleaning method	Water
	Application method	Spatula

Drying 25° C	Exterior:	30 minutes
	Dry to the touch:	2 hours
	Completely dry:	6 hours
Cold resistance		Until -30°C tested
Shelf life		Base: 12 months – Hardener: 12 months
		Do not apply in temperature below +8°C and relative humidity higher 70-75%
Standard Packaging		15 kg - 5 kg. – 1 kg.

Note The product must be stored tightly closed at temperatures not lower than 8 ° C and not above 35 ° C.; strictly avoid exposure to air and moisture of the open containers. Climatic conditions influence on hardening process, chemical resistance and mechanical properties of the finished product, it is recommended to heat the atmosphere during cold and wet weather.

Make sure before application that the temperature of the environment to be treated is between the 8-28 ° C, Relative Humidity Max 70% and humidity of the floor Max 7%.



Linea: Rivenditori Numero : 13 Revisione: 1 Anno : Aprile 2013

Rules for Application **Preparation of surfaces**

Clean well avoiding leaving dust, let it dry completely avoiding leaving visible stains. The surface should be well prepared and painted. Atriafloor Protettivo is used not only as a shield for surfaces painted or treated with Atriafloor.

Application method

Apply two coats within an interval of 12 hours.

Note: If the mixture or dosage of the base and hardener are not properly implemented, will alter the final hardening process and the physical-chemical final features. The product can be restored any time thanks to its high capacity of maintenance and permanent self-adhesion.

Recommended for Atriafloor

Not recommended for Contact with harsh solvents, concentrated bases and acids, floors with evident moisture presence.

Recommended finish Non applicable

- Safety Information**
- The base and hardener are classified eyes and skin irritants.
 - For the transportation and application you must comply with current safety and cleaning standards.
 - For more information refer to the Material Safety Data Sheet.

(*) The information, although we consider reliable, should be considered as indicative, the company reserves the right to change it without previous notice. The use of this information does not imply any responsibility on our part, including the violation of any license. It is the responsibility of users to check in advanced the suitability of the product for the specific uses. For clarification or questions regarding specific products, please contact the chief technician of the laboratory.